



1 plan

Montag 29.08.2011



B0811045 Rs(40.5°, 532+589nm) > 95% ... - Transmissionsmessung und Fit



Reflexion unter 40.5° aus obigem Fit berechnet



532 nm : 91.2, 98.7, 94.9 %
589 nm : 82.9, 98.3, 90.6 %
635 nm : 1.6, 4.1, 2.8 %
2000 nm : 0, 1.4, 0.7 %

B0811043 Rs(40.5°, 532+589nm) > 95% ... - Transmissionsmessung und FitReflexion unter 40.5° aus obigem Fit berechnet

532 nm : 91.2, 98.7, 95 %
 589 nm : 81.8, 98.2, 90 %
 635 nm : 1.5, 4.2, 2.8 %
 2000 nm : 0, 1.4, 0.7 %